

XOANONS® Dispersing agent

Model number

XOANONS®WE-D265R

Incorporation

Should be incorporated to the mill base before pigments adding.

Specification

Composition	High M.W. block style copolymer
	solution with pigment affinity groups
Appearance	Yellowish to brownish red clear
	liquid
Solvent	Dibasic ester
Active substance	45%
Density	1.04-1.08g/ml(25±1)°C
Viscosity	6-30s(Tu-4 viscometer)(25 ± 0.2) °C
Flash point	>100°C

Note: This datasheet is intended to give typical results, not standard. Subject to COA.

Suggest addition

Inorganic pigment	1-10%
Organic pigment	15-35%
Carbon black	30-100%

Storage stability

Keep intact 24 months in original package. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

Application system

Solvent-based paint and ink

package

25KG / 180KG

Properties

- Provide good color rendering for organic pigments.
 Good black tone and viscosity-reduction in dispersing high pigment carbon black.
- It's suitable thermoplastic acrylic resin system.