

# XOANONS® Fluorine surfactant

## Model number

XOANONS®WE-D9053R

## Specification

Composition	Fluorocarbon copolymer solution
Appearance	Transparent to slight yellowish clear liquid
Solvent	Dibasic ester
Active substance	50%
Density	1.26-1.30g/ml(25±1)°C
Viscosity	6-25s(Tu-4 viscometer)(25±0.2)°C
Flash point	>100°C

Note: This datasheet is intended to give typical results, not standard. Subject to COA.

## Application system

Solvent-based

## Properties

- Good long-wave leveling. Prevent orange peel phenomenon.
- Excellent ability of anti-cratering.
- Fast leveling speed.
- High temperature resistance. Could recoating.
- In systems where silicone additives cannot be used, they are often used as anti-shrinkage additives.

## Incorporation

Should be diluted with suitable solvent. Could be added at any stage of the production process, including post addition.

## Suggest addition

Addition to total formulation      0.05-0.5%

## Storage stability

Keep intact 24 months in original package. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

## Applicate recommendation

Transparency in varnish	3
Defoaming	3
Dynamic surface tension	4
Static surface tension	4
Slip	5

0=unavailable 5=very effective

## package

25KG / 180KG